

**ITEM - CHIP SEAL COAT**

The Chip Seal Coat shall be as specified in Section 404 of the Standard Specifications, and Contracts and Specifications Stored Spec. "404BITUM."

The gradation of cover material shall meet the requirements for Class 2.

The type of bituminous material shall be \* and shall be applied at the approximate rate of \* gallons per square yard.

Cover material shall be applied at the rate of approximately \* cubic yards per square yard.

The estimated haul distance for the cover material is \*\* miles.

The average elevation of the roadway for this project is \_ feet.

DESIGNER:

\* To be supplied by the Bituminous Engineer. The following guidelines apply:

Typically, the type of bituminous material is CRS-2. For estimating purposes, the application rate of the bituminous material is typically 0.45 gallons per square yard. Typically, the cover material is estimated at 0.01 cubic yards per square yard.

\*\* To be supplied by the Geotechnical Site Supervisor.