

Evaluation Table

PEP ID:	XXXXX
Manufacturer:	Name of Manufacturer
Product Name:	Name of Product

1011 Joint Materials

1011 Joint Sealant (Hot Applied) - Type III

ADOT Standard Specification: 1011-3

Responsible Section: Materials Group

Material Property	Specification/ Test Method	Requirement	Results	Pass/ Fail
Cone Penetration @ 25 °C max	ASTM D6690 ASTM D5329	90		
Softening Point, min, °C	ASTM D6690 ASTM D36	80		
Bond, water immersed	ASTM D6690 ASTM D5329	Three 12.5 ± 0.2 mm specimens pass 3 cycles at 50 % ext. at -29 °C		
Resilience, min, %	ASTM D6690 ASTM D5329	60		
Oven Aged Resilience, min, %	ASTM D6690 ASTM D5329	60		
Asphalt Compatibility	ASTM D6690 ASTM D5329	Pass		
Packaging	1011-3	The minimum ambient temperature during application and ambient temperatures under various storage conditions shall be clearly marked on the container.		