

Evaluation Table:

<b>PEP ID:</b>	
<b>Manufacturer:</b>	
<b>Product Name:</b>	

1017 – Non-Shrink Grout  
 ADOT Specifications: 1017-1, 1017-4

<b>Material Property</b>	<b>Specification/ Test Method</b>	<b>Requirement</b>	<b>Results</b>	<b>Pass/ Fail</b>
Slant shear compressive strength, min, psi	1017-4	1,000 psi at 7 days		
	ASTM C882	1,500 psi at 28 days		
Vicat time of set	1017-4 AASHTO T 131	Time of final setting shall be within 25% or 10 minutes of the manufacturer's set time. The final set time shall be a maximum of 8 hours		
Compressive strength, min, psi	1017-4	2,500 psi at 7 days		
	ASTM C1107	5,000 psi at 28 days		
Expansion, max, %	1017-4 ASTM C1107	0.4% at 3-day		
		0.4% at 14-day		
		0.4% at 28-day		
Shrinkage, max, %	1017-4 ASTM C1107	0.0% at 28 days		