

Evaluation Table

PEP ID:	XXXXXX
Manufacturer:	Name of Manufacturer
Product Name:	Name of Product

400 – Asphalt Release Agents

400 – Asphalt Release Agents

ADOT Standard Specification: 407-7.04, 408-4.03, 409-3.01, 414-7.04, 415-6, 416-6, 417-6

Additional Specification: AASHTO T 383 formerly TP 102

Responsible Section: Materials Group

Material Property	Specification/ Test Method	Requirement	Results	Pass/ Fail
NTPEP Evaluation	407-7.04, 408-4.03, 409-3.01, 414-7.04, 415-6, 416-6, 417-6	Only release agents evaluated through NTPEP are acceptable for use.		
Asphalt Stripping Test* Diluted	AASHTO T 383	No Stripping*		
Asphalt Stripping Test* Non-Diluted (Full Strength)	AASHTO T 383	No Stripping*		
Mixture Slide Test, average mass of asphalt mixture retained on the metal plate**	AASHTO T 383	10 g retained, Max		
Asphalt Performance Test, % of asphalt binder retained on the metal plate	AASHTO T 383	Less than or equal to 10.0% after the third cycle		

*AASHTO baseline photos for the Asphalt Stripping Tests are included in this ADOT Product Evaluation Program report, in addition to product NTPEP test photos for comparison.

**NTPEP has recently discontinued this test. Products submitting NTPEP reports without this test result included will be marked as N/A.