#### ARIZONA DEPARTMENT OF TRANSPORTATION \* MATERIALS GROUP



1221 NORTH 21ST AVENUE PHOENIX, ARIZONA 85009-3740 PHONE (602) 712 - 7231

#### POLICY AND PROCEDURE DIRECTIVE

James P. Delton Assistant State Engineer

| TO: ALL MANUAL HOLDERS  | PPD NO. 13a     |
|---|-----------------|
| SUBJECT:  | EFFECTIVE DATE: |
| CERTIFICATION AND ACCEPTANCE OF<br>HYDRAULIC CEMENTS, FLY ASH, NATURAL<br>POZZOLAN, SILICA FUME, AND LIME | April 14, 2010  |

#### 1. GENERAL

- 1.1 This Policy and Procedure Directive outlines the procedures to be followed for certification and acceptance of hydraulic cements, fly ash, natural pozzolan, silica fume, and lime.
- 1.2 This Policy and Procedure Directive modifies the certification procedures for hydraulic cements, fly ash, natural pozzolan, and lime. It shall be used in conjunction with the requirements of Subsection 106.05 of the Specifications.
- 1.3 The certification and acceptance of hydraulic cements, fly ash, natural pozzolan, or lime for use in Portland cement concrete or asphaltic concrete is performed as specified in Section 2.
- 1.4 The certification and acceptance of silica fume for use in Portland cement concrete is performed as specified in Section 3.
- 1.5 The certification and acceptance of lime or hydraulic cement for use in soil stabilization (Lime Treated Subgrade, Cement Treated Subgrade, or Cement Treated Base) is performed as specified in Section 4.
- 1.6 The acceptance of Portland cement and hydrated lime for use in mortar or grout is performed as specified in Section 5.

# 2. CERTIFICATION AND ACCEPTANCE OF HYDRAULIC CEMENTS, FLY ASH, NATURAL POZZOLAN, OR LIME FOR USE IN PORTLAND CEMENT CONCRETE OR ASPHALTIC CONCRETE

2.1 Hydraulic cement, fly ash, and natural pozzolan used in Portland cement concrete shall conform to the requirements of Section 1006 of the Specifications.

2.2 Portland cement, blended hydraulic cement, and hydrated lime used as a mineral admixture in asphaltic concrete shall conform to the following:

| Material                          | Requirement |
|-----------------------------------|-------------|
| Portland Cement, Type I or II     | ASTM C 150  |
| Blended Hydraulic Cement, Type IP | ASTM C 595  |
| Hydrated Lime                     | ASTM C 1097 |

- 2.3 The certification and acceptance of hydraulic cements, fly ash, natural pozzolan, or lime for use in Portland cement concrete or asphaltic concrete will be on the basis of the material originating from an <u>Approved Materials Source</u>.
- 2.4 Approved Materials Source Lists for "Hydraulic Cements", "Fly Ash and Natural Pozzolan", and "Lime (mineral admixture for asphaltic concrete)" are maintained by Materials Group, Structural Materials Testing Section. Current lists are available on the Materials Group, Structural Materials Testing Section homepage through the ADOT intranet (ADOTNet) and the ADOT internet website.
- 2.5 Project personnel shall verify that materials being used on their project are on the current Approved Materials Source List.
- 2.6 Certificates of Compliance and Certificates of Analysis are not required to be submitted with deliveries of material.
  - 2.7 No samples of hydraulic cement, fly ash, natural pozzolan, or lime are required.
- 2.7.1 The Department reserves the right to sample and test material for acceptance from any source without notification.
- 2.8 Source approval of hydraulic cement, fly ash, natural pozzolan, or lime producers/suppliers will be based on the satisfactory submittal to the Materials Group, Structural Materials Testing Engineer, on a monthly and timely basis, of the following:
  - 2.8.1 A Certificate of Compliance which lists the lots produced during that month.
- 2.8.2 A separate Certificate of Analysis for each lot shown on the corresponding Certificate of Compliance for that month.
- 2.8.3 Certificates of Compliance and Certificates of Analysis shall be submitted in electronic format (pdf) to the Structural Materials Testing Engineer at "cert@azdot.gov".
- 2.9 Examples of typical Certificates of Compliance and Certificates of Analysis are given in the attachments to this Policy and Procedure Directive.

#### CERTIFICATION AND ACCEPTANCE OF HYDRAULIC CEMENTS, FLY ASH, NATURAL POZZOLAN, SILICA FUME, AND LIME

- 2.9.1 Attachment #1 gives an example of a Certificate of Compliance for cement.
- 2.9.2 Attachment #2 gives an example of a Certificate of Analysis for cement.
- 2.9.3 Attachment #3 gives an example of a Certificate of Compliance for fly ash.
- 2.9.4 Attachment #4 gives an example of a Certificate of Analysis for fly ash.
- 2.9.5 Certificates of Compliance and Certificates of Analysis for natural pozzolan would be similar to Certificates of Compliance and Certificates of Analysis for fly ash.
  - 2.9.6 Attachment #5 gives an example of a Certificate of Compliance for lime.
  - 2.9.7 Attachment #6 gives an example of a Certificate of Analysis for lime.
- 2.10 To maintain an active status on the Approved Materials Source List, the producer/supplier shall, on a monthly and timely basis, provide either the required Certificates specified above, or other documentation described below.
- 2.10.1 If no materials are produced during any given monthly reporting period, the producer/supplier shall so notify the Structural Materials Testing Engineer by email at "cert@azdot.gov".
- 2.10.2 If no materials are produced during any given monthly reporting period, but materials are shipped from a previously certified lot of material, the producer/supplier shall so notify the Structural Materials Testing Engineer by email at "cert@azdot.gov".
- 2.10.3 If there is a temporary (more than one month) stop in production of materials from a specific source, the producer/supplier shall so notify the Structural Materials Testing Engineer by email at "cert@azdot.gov".
- 2.11 If there is a permanent stop in production of materials from a specific source, the producer/supplier shall so notify the Structural Materials Testing Engineer by email at "cert@azdot.gov".
- 2.12 The suspension of source approval shall be instituted for any of the following reasons. The Structural Materials Testing Engineer will notify the producer/supplier in writing (by letter or email) of such suspension.
  - (a) The producer/supplier provides materials from an approved source which fail to meet specification requirements to an ADOT project.

- (b) The producer/supplier fails to provide the required documents to the Department as specified for the source approval on a monthly and timely basis.
- 2.12.1 Any suspension shall be in effect until such time that the hydraulic cement, fly ash, natural pozzolan, or lime producer/supplier can demonstrate that the deficiency in the material has been corrected and the product meets specification requirements, and/or the requirements for submittal of the required documents have been met. The Structural Materials Testing Engineer will notify the producer/supplier in writing (by letter or email) of the removal of such suspension.

## 3. CERTIFICATION AND ACCEPTANCE OF SILICA FUME FOR USE IN PORTLAND CEMENT CONCRETE

- 3.1 Silica fume used in Portland cement concrete shall conform to the requirements of ASTM C 1240.
- 3.2 A Certificate of Compliance conforming to the requirements of Subsection 106.05 shall be submitted for each delivery of silica fume.
  - 3.3 No samples of silica fume are required.
- 3.3.1 The Department reserves the right to sample and test material which has been accepted on the basis of a Certificate of Compliance.

# 4. CERTIFICATION AND ACCEPTANCE OF LIME OR HYDRAULIC CEMENT FOR USE IN SOIL STABILIZATION (LIME TREATED SUBGRADE, CEMENT TREATED SUBGRADE, OR CEMENT TREATED BASE)

- 4.1 Lime used in soil stabilization shall conform to the requirements of ASTM C 977 and Section 301 of the Specifications.
- 4.2 Hydraulic cement used in soil stabilization shall conform to the requirements of Section 302 or Section 304 of the Specifications.
- 4.3 If desired by the producer/supplier, the acceptance and certification of hydraulic cement used in soil stabilization may be performed as specified in Section 2. Otherwise, a Certificate of Compliance conforming to the requirements of Subsection 106.05 shall be submitted for each delivery of hydraulic cement.
- 4.4 A Certificate of Compliance conforming to the requirements of Subsection 106.05 shall be submitted for each delivery of lime.

- 4.5 No samples of lime or hydraulic cement are required.
- 4.5.1 The Department reserves the right to sample and test material as deemed necessary by the Engineer.

## 5. ACCEPTANCE OF PORTLAND CEMENT AND HYDRATED LIME FOR USE IN MORTAR OR GROUT

- 5.1 Portland cement used in mortar or grout shall conform to the requirements of Section 1006 of the ADOT Specifications.
- 5.2 Hydrated lime used in mortar or grout shall conform to the requirements of ASTM C 207, Type N.
  - 5.3 Certificates of Compliance or Certificates of Analysis are not required.
- 5.4 Portland cement and hydrated lime used in mortar or grout shall be approved by the Engineer.
- 5.4.1 If desired by the producer/supplier, the acceptance and certification of Portland cement used in mortar and grout may be performed as specified in Section 2.
  - 5.5 No samples of Portland cement or hydrated lime are required.
- 5.5.1 The Department reserves the right to sample and test material as deemed necessary by the Engineer.

James P. Delton, P.E. Assistant State Engineer Materials Group

Attachments (6)

#### ACME CEMENT COMPANY

9876 N. Notled Drive Bigtown, AZ 85555 Phone No. 602-555-4321

#### **CERTIFICATE OF COMPLIANCE**

Date: April 29, 2010

Material: Type II/V Portland Cement

Source: Newton Plant

The following lots of Type II/V Portland Cement have been produced during the month of **March 2010** at the Newton Plant in Bigtown, Arizona.

| Lot Number |
|------------|
| 0011562    |
| 0011563    |
| 0011564    |
| 0011565    |
| 0011566    |
| 0011567    |
| 0011568    |
| 0011569    |
| 0011570    |
|            |

I hereby certify that the Type II/V Portland Cement produced in the lots listed above meets or exceeds the requirements specified in ASTM C 150 and Subsection 1006-2.01 of the Arizona Department of Transportation Specifications.

Respectfully,

(Signature)
Billy B. Bop
General Manager

#### ACME CEMENT COMPANY

9876 N. Notled Drive Bigtown, AZ 85555 Phone No. 602-555-4321

#### **CERTIFICATE OF ANALYSIS**

Date: April 29, 2010

Material: Type II/V Portland Cement

Source: Newton Plant

The following are the test results for Lot Number 0011566 of Type II/V Portland Cement produced during the month of March 2010 at the Newton Plant in Bigtown, Arizona.

| TESTS  | RESULTS | SPECIFICATIONS |            |
|--|---------|----------------|------------|
|  |         | TYPE II        | TYPE V     |
| Silicon Dioxide (SiO <sub>2</sub> ), %                 | 20.9    |                |            |
| Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ), %    | 4.0     | 6.0 max.       |            |
| Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ), %        | 3.7     | 6.0 max.       | <i></i>    |
| Calcium Oxide (CaO), %                                 | 63.5    |                |            |
| Magnesium Oxide (MgO), %                               | 2.8     | 6.0 max.       | 6.0 max.   |
| Sulfur Trioxide (SO <sub>3</sub> ), %                  | 2.9     | 3.0 max.       | 2.3 max.*  |
| Loss on Ignition, %                                    | 2.6     | 3.0 max.       | 3.0 max.   |
| Insoluble Residue, %                                   | 0.52    | 0.75 max.      | 0.75 max.  |
| Equivalent Alkalies, %                                 | 0.56    | 0.60 max.      | 0.60 max.  |
| Carbon Dioxide, (CO <sub>2</sub> ), %                  | 1.7     |                |            |
| Limestone, %   | 4.5     | 5.0 max.       | 5.0 max    |
| Calcium Carbonate, (CaCO <sub>3</sub> in Limestone), % | 88      | 70 min.        | 70 min.    |
| Potential Composition:                                 |         |                |            |
| C <sub>3</sub> S, %                                    | 51      |                |            |
| C <sub>2</sub> S, %                                    | 21      |                |            |
| C <sub>3</sub> A, %                                    | 4       | 8 max.         | 5 max      |
| C <sub>4</sub> AF, %                                   | // 11   |                |            |
| $C_3S + 4.75(C_3A), \%$                                | 70      | 100 max.       |            |
| $C_4AF + 2(C_3A), \%$                                  | 19      |                | 25 max.    |
| Physical Analysis:                                     |         |                |            |
| Blaine Fineness, m²/kg                                 | 406     | 280 min.       | 280 min.   |
| Air Content, %   | 7       | 12 max.        | 12 max.    |
| Autoclave Expansion, %                                 | 0.03    | 0.80 max.      | 0.80 max.  |
| 3-Day Compressive Strength, psi                        | 3980    | 1450 min.      | 1160 min.  |
| 7-Day Compressive Strength, psi                        | 5060    | 2470 min.      | 2180 min.  |
| 28-Day Compressive Strength, psi                       | 6350    |                | 3050 min.  |
| Autoclave Expansion, %                                 | 0.03    | 0.80 max.      | 0.80 max   |
| Initial Vicat, minutes                                 | 120     | 45 min.        | 45 min.    |
| Mortar Bar Expansion, %                                | 0.010   | 0.020 max.     | 0.020 max. |

<sup>\*</sup>Must conform to ASTM C 1038 mortar bar expansion limit of 0.020% if the maximum percent specified for  $SO_3$  is exceeded.

I certify that Lot Number 0011566 of Type II/V Portland Cement, produced during the month of March 2010 at the Newton Plant, meets or exceeds the requirements specified in ASTM C 150 and Subsection 1006-2.01 of the Arizona Department of Transportation Specifications.

| I        | ,           |  |
|----------|-------------|--|
|          |             |  |
|          | (Signature) |  |
| Billy B. | Вор         |  |
| General  | Manager     |  |

Respectfully

#### FLYASH R' US

1234 N. Gwegowy Way Littletown, AZ 85111 Phone No. 602-555-6789

#### **CERTIFICATE OF COMPLIANCE**

Date: May 13, 2010 Material: Class F Fly Ash Source: Ashley Plant

The following lots of Class F Fly Ash have been produced during the month of **March 2010** at the Ashley Plant in Littletown, Arizona.

| Lot Number |
|------------|
|            |
| 041562     |
| 041563     |
| 041564     |
| 041565     |
| 041566     |
| 041567     |
| 041568     |
| 041569     |
| 041570     |
|            |

I hereby certify that the Class F Fly Ash produced in the lots listed above meets or exceeds the requirements specified in ASTM C 618 and Subsection 1006-2.04 of the Arizona Department of Transportation Specifications.

Respectfully,

(Signature)
Mat Erial
President

#### FLYASH R' US

1234 N. Gwegowy Way Littletown, AZ 85111 Phone No. 602-555-6789

#### **CERTIFICATE OF ANALYSIS**

Date: May 13, 2010 Material: Class F Fly Ash Source: Ashley Plant

The following are the test results for Lot Number 041567 of Class F Fly Ash produced during the month of March 2010 at the Ashley Plant in Littletown, Arizona.

| TESTS   | RESULTS | SPECIFICATIONS |
|---|---------|----------------|
| Silicon Dioxide (SiO <sub>2</sub> ), %  | 61.12   |                |
| Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ), %   | 22.09   |                |
| Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ), %   | 5.78    |                |
| Sum of SiO <sub>2</sub> , Al <sub>2</sub> O <sub>3</sub> , Fe <sub>2</sub> O <sub>3</sub> , % | 89.99   | 🌽 70 min.      |
| Calcium Oxide (CaO), %  | 4.79    |                |
| Magnesium Oxide (MgO), %  | 0,98    |                |
| Sulfur Trioxide (SO <sub>3</sub> ), %   | 0.42    | 5.0 max.       |
| Sodium Oxide (Na <sub>2</sub> O), %   | 0.87    |                |
| Potassium Oxide (K <sub>2</sub> O), %   | 1.30    |                |
| Total Alkalies (as Na <sub>2</sub> O), %  | 1.73    |                |
| Available Alkalies (as Na <sub>2</sub> O), %  | 0.50    |                |
|   |         |                |
| Moisture Content, %   | 0.03    | 3.0 max.       |
| Loss on Ignition, %   | 0.21    | 3.0 max.       |
| Amount Retained on No. 325 Sieve, %   | 26.14   | 34 max.        |
| Specific Gravity  | 2.25    |                |
| Autoclave Soundness, %  | -0.01   | 0.8 max.       |
| SAI, 7 Days, % of Control   | 76.5    | 75 min.*       |
| SAI, 28 Days, % of Control  | 95.5    | 75 min.*       |
| Water Required, % of Control  | 96.3    | 105 max.       |

<sup>\*</sup>Meeting the 7 day or 28 day Strength Activity Index will indicate specification compliance.

I certify that Lot Number 041567 of Class F fly Ash, produced during the month of March 2010 at the Ashley Plant, meets or exceeds the requirements specified in ASTM C 618 and Subsection 1006-2.04 of the Arizona Department of Transportation Specifications.

|           | (Signature) |  |
|-----------|-------------|--|
| Mat Erial | ,           |  |

Respectfully,

President

#### LIME INCORPORATED

4321 South Seger Drive Middletown, AZ 85999 Phone No. 602-555-9876

### CERTIFICATE OF COMPLIANCE

Date: April 2, 2010

Material: Hydrated Lime (ASTM C 1097)

Source: Seger Plant

The following lots of Hydrated Lime (ASTM C 1097) have been produced during the month of **March 2010** at the Seger Plant in Middletown, Arizona.

| Lot Number |
|------------|
| 030110     |
| 030810     |
| 031510     |
| 032210     |
| 032910     |

I hereby certify that the Hydrated Lime produced in the lots listed above meets or exceeds the requirements specified in ASTM C 1097.

Respectfully,

(Signature)

Barbie Que

Vice President, Quality Control

#### LIME INCORPORATED

4321 South Seger Drive Middletown, AZ 85999 Phone No. 602-555-9876

### **CERTIFICATE OF ANALYSIS**

Date: April 2, 2010

Hydrated Lime (ASTM C 1097)

Source: Seger Plant

Material:

Respectfully

The following are the test results for Lot Number 030810 of Hydrated Lime (ASTM C 1097) produced during the month of March 2010 at the Seger Plant in Middletown, Arizona.

| TESTS                                   | RESULTS | SPECIFICATIONS |
|---|---------|----------------|
| Total Calcium Oxide (CaO) and Magnesium | 97.37   | 90.0 min.      |
| Oxide (MgO), %                          | 27.57   | 50.0 mm.       |
| Carbon Dioxide, %                       | 0.69    | 5.0 max.       |
| Unhydrated CaO and MgO (Insolubles), %  | 0.90    | 5.0 max.       |
| Free Moisture of Dry Hydrates, %        | 0.40    | 2.0 max        |
|   |         |                |
| Retained on No. 30 Sieve, %             | 0.19    | 3.0 max.       |
| Retained on No. 200 Sieve, %            | 5.65    | 30 max.        |

I certify that Lot Number 030810 of Hydrated Lime produced during the month of March 2010 at the Seger Plant, meets or exceeds the requirements specified in ASTM C 1097.

| (Signature)                     |
|---------------------------------|
| Barbie Que                      |
| Vice President, Quality Control |