

## **APPENDIX C**

# **SAMPLING GUIDE SCHEDULE**

**Tables 1 through 8 (Pages 1–60) - Acceptance Sampling Guide.**

<b>Table 1</b>	<b>Soils (Pages 1-3)</b>
<b>Table 2</b>	<b>Aggregates (Pages 4-26)</b>
<b>Table 3</b>	<b>Bituminous Materials (Pages 27-34)</b>
<b>Table 4</b>	<b>Portland Cement Concrete (Pages 35-38)</b>
<b>Table 5</b>	<b>Materials Used With Portland Cement Concrete (Pages 39-42)</b>
<b>Table 6</b>	<b>Stablized Soils and Bases (Pages 43-44)</b>
<b>Table 7</b>	<b>Bituminous Mixtures (Pages 45-48)</b>
<b>Table 8</b>	<b>Miscellaneous Materials (Pages 49-60)</b>

**Table 9 (Page 61) - Illustration of Sampling Ticket and Listing  
of Codes for Purpose, Testing Lab, Size,  
and Roadway.**

**Table 10 (Pages 62–65) - Listing of Material Codes and Type  
Codes Used By FAST (Field Office  
Automation SysTem).**

**Table 11 (Pages 66-69) - Index of Materials Listed in  
Tables 1 through 8.**

This page intentionally left blank.

TABLE 1 ACCEPTANCE SAMPLING GUIDE FOR SOILS				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
203	Borrow (within 3 ft. of finished subgrade elevation)	Gradation <sup>(1)</sup>	In-Place	One per 1500 ft.
		PI <sup>(1)</sup>		
203	Embankment	Proctor Density	In-Place	One per soil type, and as needed.
		Optimum Moisture		
		Compaction	In-Place	One per 1500 ft. per lift.
	Embankment for Metal Pile Location only	pH	In-Place or Source	One per source.
		Resistivity		
203	Natural Ground for Embankment 5 ft. or less in height	Proctor Density	In-Place	One per soil type, and as needed.
		Optimum Moisture		
		Compaction	In-Place	One per 1500 ft.
(1) Independent Assurance Sampling and Testing required.				

TABLE 1 (continued) ACCEPTANCE SAMPLING GUIDE FOR SOILS				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
203	Subgrade	Proctor Density	Roadway	One per soil type, and as needed.
		Optimum Moisture		
		Compaction	Roadway	One per 1500 ft.
		Gradation <sup>(1)</sup>	Roadway	One per 1500 ft. or change in material.
		PI <sup>(1)</sup>		
203	Soil for Shoulder Build-up	Gradation	In-Place or Source	One per soil type.
		PI		
		pH		
		Soluble Salts		
		Compaction	In-Place	One per 1500 ft. or as directed by the Engineer.
501	Trench Backfill	Proctor Density	In-Place	One per soil type, and as needed.
		Optimum Moisture		
		Compaction	In-Place	One per 100 CY.
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				

TABLE 1 (continued) ACCEPTANCE SAMPLING GUIDE FOR SOILS				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
803	Granite Mulch or Decomposed Granite	Gradation	In-Place or Source	One per 10,000 CY.
804	Top Soil	Gradation <sup>(1)</sup>	In-place	Written soil analysis per source and six samples per lot [a lot is considered approximately 20,000 CY per source].
		PI <sup>(1)</sup>		
		pH <sup>(1)</sup>		
		Soluble Salts		
		Calcium Carbonate		
		Exchangeable Sodium in percent and parts per million		
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				

TABLE 2 ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
203 501  (When Contractor Quality Control <b>is not</b> a bid item.)	Structure Backfill or Pipe Backfill	Proctor Density	Stockpile	One per source, and as needed.
		Optimum Moisture		
		Compaction	In-Place	One per 75 CY.
		Resistivity	Source or Stockpile	One per source.
		pH		
		Gradation <sup>(1)</sup>	On Job Site	One per 500 CY per source.
		PI <sup>(1)</sup>		
203 501  (When Contractor Quality Control <b>is</b> a bid item.)	Structure Backfill or Pipe Backfill	Proctor Density	Stockpile	One per source, and as needed.
		Optimum Moisture		
		Compaction	In-Place	One per 100 CY.
		Resistivity	Source or Stockpile	One per source.
		pH		
		Gradation <sup>(1)</sup>	On Job Site	One per 1500 CY per source.
		PI <sup>(1)</sup>		
(1) Independent Assurance Sampling and Testing required.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
303  (When Contractor Quality Control <b>is not</b> a bid item.)	Aggregate Base Class 1, Class 2, and Class 3	Abrasion <sup>(2)</sup>	Source	One per source.
		Proctor Density	Crusher Belt or Stockpile	At start of production, then as material changes.
		Optimum Moisture		
		Compaction	Roadway	One per lift per 1000 ft.
		Fractured Coarse Aggregate Particles <sup>(1)</sup>	Stockpile	One per 10,000 tons.
		Gradation <sup>(1)</sup>	Windrow	One per 2000 tons, minimum one per shift.
		PI <sup>(1)</sup>		
<div><div>(1) Independent Assurance Sampling and Testing required.</div><div>(2) Provided Construction &amp; Materials Group concurs, historical abrasion values may be used.</div></div>				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
303  (When Contractor Quality Control <b>is</b> a bid item.)	Aggregate Base Class 1, Class 2, and Class 3	Abrasion <sup>(2)</sup>	Source	One per source.
		Proctor Density	Crusher Belt or Stockpile	At start of production, then as material changes.
		Optimum Moisture		
		Compaction	Roadway	One per lift per 1500 ft.
		Fractured Coarse Aggregate Particles <sup>(1)</sup>	Stockpile	One per 10,000 tons.
		Gradation <sup>(1)</sup>	Windrow	One per 2000 tons, minimum one per shift.
		PI <sup>(1)</sup>		
<div>(1) Independent Assurance Sampling and Testing required.</div> <div>(2) Provided Construction &amp; Materials Group concurs, historical abrasion values may be used.</div>				



TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
303  (When Contractor Quality Control <b>is not</b> a bid item.)	Aggregate Subbase Class 4, Class 5, and Class 6	Proctor Density	Crusher Belt or Stockpile	At start of production, then as material changes.
		Optimum Moisture		
		Compaction	Roadway	One per lift per 1000 ft.
	Class 4	Fractured Coarse Aggregate Particles <sup>(1)</sup>	Stockpile	One per 10,000 tons.
		Gradation <sup>(1)</sup>	Windrow	One per 2000 tons, minimum one per shift.
		PI <sup>(1)</sup>		
		Abrasion <sup>(2)</sup>	Source	One per source.
	Class 5 and Class 6	Gradation <sup>(1)</sup>	Windrow	One per 2000 tons, minimum one per shift.
		PI <sup>(1)</sup>		
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				
<sup>(2)</sup> Provided Construction & Materials Group concurs, historical abrasion values may be used.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
303  (When Contractor Quality Control <u>is</u> a bid item.)	Aggregate Subbase Class 4, Class 5, and Class 6	Proctor Density	Crusher Belt or Stockpile	At start of production, then as material changes.
		Optimum Moisture		
		Compaction	Roadway	One per lift per 1500 ft.
	Class 4	Fractured Coarse Aggregate Particles <sup>(1)</sup>	Stockpile	One per 10,000 tons.
		Gradation <sup>(1)</sup>	Windrow	One per 2000 tons, minimum one per shift.
		PI <sup>(1)</sup>		
		Abrasion <sup>(2)</sup>	Source	One per source.
	Class 5 and Class 6	Gradation <sup>(1)</sup>	Windrow	One per 2000 tons, minimum one per shift.
		PI <sup>(1)</sup>		
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				
<sup>(2)</sup> Provided Construction & Materials Group concurs, historical abrasion values may be used.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
304 305	Aggregate for Cement Treated Base or Lean Concrete Base	Gradation <sup>(1)</sup>	Stockpile	One per 2000 tons, minimum one per shift.
		Fractured Coarse Aggregate Particles <sup>(1)</sup>	Stockpile	One per 10,000 tons.
		Abrasion <sup>(2)</sup>	Source	One per source.
	for Cement Treated Base	PI <sup>(1)</sup>	Stockpile	One per 2000 tons, minimum one per shift.
	for Lean Concrete Base	Sand Equivalent <sup>(1)</sup>	Stockpile	One every other day of Lean Concrete Base production.
<p><sup>(1)</sup> Independent Assurance Sampling and Testing required.</p> <p><sup>(2)</sup> Provided Construction &amp; Materials Group concurs, historical abrasion values may be used.</p>				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
404	Cover Material	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Bulk O.D. Specific Gravity	Stockpile	One per source.
		Percent Carbonates		
		Dry Unit Weight		
		Fractured Coarse Aggregate Particles	Stockpile	One per 600 tons.
		Flakiness Index		
		Gradation <sup>(1)</sup>	Final Stockpile	One per 300 tons.
		Moisture Content	Trucks at Scale	One per 300 tons.
404 412 413 415	Blotter Material	Gradation <sup>(1)</sup>	Final Stockpile	One per stockpile.
<sup>(1)</sup> Independent Assurance Sampling and Testing required. <sup>(2)</sup> Provided Construction & Materials Group concurs, historical abrasion values may be used.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
Refer to Special Provisions	Mineral Aggregate for Micro- Surfacing	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Percent Carbonates	Stockpile	One per source.
		Gradation <sup>(1)</sup>	Final Stockpile	One prior to start of Micro-Surfacing production, and one per 300 tons
		Sand Equivalent	Stockpile	One prior to start of Micro-Surfacing production, and one per 600 tons
		Fractured Coarse Aggregate Particles		
		Uncompacted Void Content		
		Moisture Content	Trucks at Scale	One per 300 tons.
<div><div>(1)</div>Independent Assurance Sampling and Testing required.</div> <div><div>(2)</div>Provided Construction &amp; Materials Group concurs, historical abrasion values may be used.</div>				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
407	Mineral Aggregate for Asphaltic Concrete Friction Course (ACFC)	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Percent Carbonates		
		Specific Gravity		
		Gradation	Cold Feed	One prior to the start of ACFC production.
		Sand Equivalent <sup>(1)</sup>	Cold Feed or Stockpile	One prior to the start of ACFC production and one per each two days of ACFC production, minimum of two per project.
		Flakiness Index <sup>(1)</sup>		
		Fractured Coarse Aggregate Particles <sup>(1)</sup>		
		Moisture Content	Prior to mixing with mineral admixture	
		Gradation <sup>(1)</sup>	Cold Feed or Hot Bins	One per 500 tons of ACFC production, minimum of one per shift.
<sup>(1)</sup> Independent Assurance Sampling and Testing required. <sup>(2)</sup> Provided Construction & Materials Group concurs, historical abrasion values may be used.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
409	Mineral Aggregate for Asphaltic Concrete (Miscellaneous Structural)  [For Special Mix, see below.]	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Percent Carbonates (if required)		
		Sand Equivalent	Stockpile	One per source.
		Fractured Coarse Aggregate Particles		
		Moisture Content	Prior to mixing with mineral admixture	One per each two days of asphaltic concrete production.
		Gradation	Cold Feed or Hot Bins	At discretion of the Engineer.
409	Mineral Aggregate for Asphaltic Concrete (Miscellaneous Structural – Special Mix)	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Percent Carbonates (if required)		
		Sand Equivalent <sup>(1)</sup>	Stockpile	One per source.
		Uncompacted Void Content <sup>(1)</sup>	Stockpile	One prior to start of asphaltic concrete production.
		Fractured Coarse Aggregate Particles <sup>(1)</sup>	Cold Feed or Stockpile	One per each two days of asphaltic concrete production, minimum of two per project.
		Moisture Content	Prior to mixing with mineral admixture	One per each two days of asphaltic concrete production.
		Gradation	(See Bituminous Mixture requirements for Asphaltic Concrete (Miscellaneous Structural - Special Mix) on Page 45.)	
		<div><div>(1) Independent Assurance Sampling and Testing required.</div><div>(2) Provided Construction &amp; Materials Group concurs, historical abrasion values may be used.</div></div>		

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
411	Mineral Aggregate for Asphaltic Concrete Friction Course (ACFC) - Miscellaneous	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Percent Carbonates		
		Sand Equivalent	Stockpile	One per source.
		Flakiness Index		
		Fractured Coarse Aggregate Particles		
		Moisture Content	Prior to mixing with mineral admixture	One per each two days of ACFC production.
		Gradation	Cold Feed or Hot Bins	At the discretion of the Engineer.
413	Mineral Aggregate for Asphaltic Concrete (Asphalt-Rubber) [AR-AC]	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Percent Carbonates (if required)		
		Specific Gravity	Stockpile	One per source.
		Gradation	Cold Feed	One prior to the start of AR-AC production.
		Sand Equivalent <sup>(1)</sup>	Cold Feed or Stockpile	One prior to the start of AR-AC production and one per each two days of AR-AC production, minimum of two per project.
		Fractured Coarse Aggregate Particles <sup>(1)</sup>		
		Moisture Content	Prior to mixing with mineral admixture	One per each two days of AR-AC production.
			Gradation <sup>(1)</sup>	Cold Feed or Hot Bins
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				
<sup>(2)</sup> Provided Construction & Materials Group concurs, historical abrasion values may be used.				



TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
414	Mineral Aggregate for Asphaltic Concrete Friction Course (Asphalt-Rubber) [AR-ACFC]	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Specific Gravity	Stockpile	One per source.
		Percent Carbonates		
		Gradation	Cold Feed	One prior to the start of AR-ACFC production.
		Sand Equivalent <sup>(1)</sup>	Cold Feed or Stockpile	One prior to the start of AR-ACFC production and one per each two days of AR-ACFC production, minimum of two per project.
		Fractured Coarse Aggregate Particles <sup>(1)</sup>		
		Flakiness Index <sup>(1)</sup>		
		Moisture Content	Prior to mixing with mineral admixture	
		Gradation <sup>(1)</sup>	Cold Feed or Hot Bins	One per 500 tons of AR-ACFC production, minimum of one per shift.
<p><sup>(1)</sup> Independent Assurance Sampling and Testing required.</p> <p><sup>(2)</sup> Provided Construction &amp; Materials Group concurs, historical abrasion values may be used.</p>				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
415	Mineral Aggregate for Asphaltic Concrete (Asphalt- Rubber) - End Product [AR-AC]	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Percent Carbonates (if required)		
		Sand Equivalent	Stockpile	One at least five working days prior to start of AR-AC production.
		Fractured Coarse Aggregate Particles		
		Uncompacted Void Content		
		Ignition Furnace Calibration		
		Sand Equivalent <sup>(1)</sup>	Cold Feed or Stockpile	One per each two days of AR-AC production, minimum of two per project.
		Fractured Coarse Aggregate Particles <sup>(1)</sup>		
		Uncompacted Void Content <sup>(1)</sup>		
		Moisture Content	Prior to mixing with mineral admixture	
	Gradation	(See Bituminous Mixture requirements for Asphaltic Concrete (Asphalt-Rubber) - End Product on Page 46.)		
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				
<sup>(2)</sup> Historical abrasion values may be used provided testing was conducted within the past two years.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
416	Mineral Aggregate for Asphaltic Concrete - End Product <b>[without reclaimed asphalt pavement (RAP)]</b>  (See Page 18 for mixes with RAP.)	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Percent Carbonates (if required)		
		Sand Equivalent	Stockpile	One at least five days prior to start of asphaltic concrete production.
		Fractured Coarse Aggregate Particles		
		Uncompacted Void Content <b>(Special Mix only)</b>		
		Ignition Furnace Calibration		
		Sand Equivalent <sup>(1)</sup>	Cold Feed or Stockpile	One per each two days of asphaltic concrete production, minimum of two per project.
		Fractured Coarse Aggregate Particles <sup>(1)</sup>		
		Uncompacted Void Content <sup>(1)</sup> <b>(Special Mix only)</b>		
		Moisture Content	Prior to mixing with mineral admixture	
		Gradation	(See Bituminous Mixture requirements for Asphaltic Concrete - End Product on Page 47.)	
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				
<sup>(2)</sup> Historical abrasion values may be used provided testing was conducted within the past two years.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
416	Mineral Aggregate for Asphaltic Concrete - End Product <b>[with reclaimed asphalt pavement (RAP)]</b> See PPD <sup>(3)</sup> .  (See Page 17 for mixes without RAP.)	Abrasion <sup>(2)</sup> (Virgin Agg. and RAP Agg. separately)	Source or Stockpile	One per source.
		Percent Carbonates (if required) (Composite of Virgin Agg. and RAP Agg.)		
		Sand Equivalent (Virgin Agg. only)	Stockpile	One at least five days prior to start of asphaltic concrete production.
		Fractured Coarse Aggregate Particles (Composite of Virgin Agg. and RAP Agg.)		
		Uncompacted Void Content ( <b>Special Mix only</b> ) (Virgin Agg. only)		
		Ignition Furnace Calibration (Virgin Agg., RAP Agg., and RAP material)		
		Gradation, Binder Content <sup>(1)</sup> , and Moisture Content of RAP material	Individual stockpiles (belt cut may be used for single stockpile)	One per each lot of asphaltic concrete production.
		Sand Equivalent <sup>(1)</sup> (Virgin Agg. only)	Cold Feed or Stockpile	One per each two days of asphaltic concrete production, minimum of two per project.
		Fractured Coarse Aggregate Particles <sup>(1)</sup> (Composite of Virgin Agg. and RAP Agg. obtained from Arizona Test Method 428)		
		Uncompacted Void Content <sup>(1)</sup> <b>(Special Mix only)</b> (Virgin Agg. only)		
	Moisture Content	Prior to mixing with mineral admixture		
	Gradation	(See Bituminous Mixture requirements for Asphaltic Concrete - End Product on Page 47.)		
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				
<sup>(2)</sup> Historical abrasion values may be used provided testing was conducted within the past two years.				
<sup>(3)</sup> ADOT Materials Practice and Procedure Directive.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
417	Mineral Aggregate for Asphaltic Concrete (End Product) SHRP Volumetric Mix [without reclaimed asphalt pavement (RAP)]  (See Page 20 for mixes with RAP.)	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Percent Carbonates (if required)		
		Sand Equivalent	Stockpile	One at least five days prior to start of asphaltic concrete production.
		Fractured Coarse Aggregate Particles		
		Uncompacted Void Content		
		Ignition Furnace Calibration		
		Sand Equivalent <sup>(1)</sup>	Cold Feed or Stockpile	One per each two days of asphaltic concrete production, minimum of two per project.
		Fractured Coarse Aggregate Particles <sup>(1)</sup>		
		Uncompacted Void Content <sup>(1)</sup>		
		Moisture Content	Prior to mixing with mineral admixture	
	Gradation	(See Bituminous Mixture requirements for Asphaltic Concrete (End Product) SHRP Volumetric Mix on Page 48.)		
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				
<sup>(2)</sup> Historical abrasion values may be used provided testing was conducted within the past two years.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
417	Mineral Aggregate for Asphaltic Concrete (End Product) SHRP Volumetric Mix [with reclaimed asphalt pavement (RAP)] See PPD <sup>(3)</sup> .  (See Page 19 for mixes without RAP.)	Abrasion <sup>(2)</sup> (Virgin Agg. and RAP Agg. separately)	Source or Stockpile	One per source.
		Percent Carbonates (if required) (Composite of Virgin Agg. and RAP Agg.)		
		Sand Equivalent (Virgin Agg. only)	Stockpile	One at least five days prior to start of asphaltic concrete production.
		Fractured Coarse Aggregate Particles (Composite of Virgin Agg. and RAP Agg.)		
		Uncompacted Void Content (Virgin Agg. only)		
		Ignition Furnace Calibration (Virgin Agg., RAP Agg., and RAP material)		
		Gradation, Binder Content <sup>(1)</sup> , and Moisture Content of RAP material	Individual stockpiles (belt cut may be used for single stockpile)	One per each lot of asphaltic concrete production.
		Sand Equivalent <sup>(1)</sup> (Virgin Agg. only)	Cold Feed or Stockpile	One per each two days of asphaltic concrete production, minimum of two per project.
		Fractured Coarse Aggregate Particles <sup>(1)</sup> (Composite of Virgin Agg. and RAP Agg. obtained from Arizona Test Method 428)		
		Uncompacted Void Content <sup>(1)</sup> (Virgin Agg. only)		
	Moisture Content	Prior to mixing with mineral admixture		
	Gradation	(See Bituminous Mixture requirements for Asphaltic Concrete (End Product) SHRP Volumetric Mix on Page 48.)		
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				
<sup>(2)</sup> Historical abrasion values may be used provided testing was conducted within the past two years.				
<sup>(3)</sup> ADOT Materials Practice and Procedure Directive.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
Refer to Special Provisions	Mineral Aggregate for Asphaltic Concrete - Miscellaneous Paving	Abrasion <sup>(2)</sup>	Source or Stockpile	One per source.
		Sand Equivalent	Stockpile	One per source.
		Gradation	Cold Feed or Hot Bins	At discretion of the Engineer.
501	Bedding Material for Pipe	Gradation <sup>(1)</sup>	Source or Stockpile	One per 300 CY per source.
		PI <sup>(1)</sup>		One per source.
		pH <sup>(1)</sup>		
		Resistivity <sup>(1)</sup>	Source or Stockpile	One per source, and as needed.
		Proctor Density		
		Optimum Moisture	In-Place	One every 50 CY.
		Compaction		
501	Filter Material for Perforated Pipe	Gradation <sup>(1)</sup>	Source or Stockpile	One per 300 CY per source.
<sup>(1)</sup> Independent Assurance Sampling and Testing required. <sup>(2)</sup> Provided Construction & Materials Group concurs, historical abrasion values may be used.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
501	Plating Material for Pipe Ends	Gradation	Source or Stockpile	One per source, and as needed.
		PI		
		Proctor Density		
		Optimum Moisture		
		Compaction	In-Place	One every 50 CY.
702	Crash Barrel Sand	Gradation	Plant or Site	One per each attenuator system location.
		Dry Unit Weight per cubic foot		
		Moisture Content		
	Sand and Rock Salt Mixture (when Sand Barrel Crash Cushions are installed at elevations above 3,000 feet)	Percent Rock Salt		
808	Bedding Material for Polyvinyl Chloride (PVC) Irrigation Pipe	Gradation	Source or Stockpile	One per source.



TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
913	Rock for Wire Tied Riprap, Gabions, Riprap (Slope Mattress), and Rail Bank Protection	Specific Gravity	Source	One per source.
		Gradation (visual)	Project	One per 1/2 shift.
	Rock for Grouted Riprap and Dumped Riprap	Specific Gravity	Source	One per source.
		Gradation	Project	One per 1/2 shift.

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1006	Fine Aggregate for Portland Cement Concrete (PCC) Classes P, S, and B	Gradation <sup>(1)</sup>	Batch Plant Conveyer Belt or Stockpile	One every other day of PCC production.
		Sand Equivalent <sup>(1)</sup>		
		Soundness [when used in concrete over 4500 ft. elevation]	Stockpile	One per source. For evaluation of concrete aggregate sources, see PPD <sup>(3)</sup> .
		Organic Impurities		
		Mortar Strength		
		Deleterious Substances [Clay Lumps and Friable Particles; Lightweight Particles]	Stockpile	At the discretion of Materials Group. For evaluation of concrete aggregate sources, see PPD <sup>(3)</sup> .
<div><div><sup>(1)</sup> Independent Assurance Sampling and Testing required.</div><div><sup>(3)</sup> ADOT Materials Practice and Procedure Directive.</div></div>				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1006	Coarse Aggregate for Portland Cement Concrete (PCC) Classes P, S, and B	Gradation <sup>(1)</sup>	Batch Plant Conveyer Belt or Stockpile	One every other day of PCC production.
		Soundness [when used in concrete over 4500 ft. elevation]	Stockpile	One per source. For evaluation of concrete aggregate sources, see PPD <sup>(3)</sup> .
		Abrasion <sup>(2)</sup>		
		Deleterious Substances [Clay Lumps and Friable Particles; Lightweight Particles; Material Passing No. 200 Sieve]	Stockpile	With the exception of “Material Passing No. 200 Sieve”, at the discretion of Materials Group. For evaluation of concrete aggregate sources, see PPD <sup>(3)</sup> .
		Fractured Coarse Aggregate Particles	Stockpile	One per source.
<sup>(1)</sup> Independent Assurance Sampling and Testing required. <sup>(2)</sup> Provided Construction & Materials Group concurs, historical abrasion values may be used. <sup>(3)</sup> ADOT Materials Practice and Procedure Directive.				

TABLE 2 (continued) ACCEPTANCE SAMPLING GUIDE FOR AGGREGATES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
Refer to Special Provisions	Aggregate for Arrestor Bed	Abrasion <sup>(2)</sup>	Screen Belt or Stockpile	One per source.
		Specific Gravity		
		Gradation <sup>(1)</sup>	Screen Belt or Stockpile	One per shift.
		Fractured Coarse Aggregate Particles <sup>(1)</sup>		
		Flakiness Index <sup>(1)</sup>		
Refer to Special Provisions	Aggregate for Soil-Cement Bank Protection or Cement Stabilized Alluvium	Gradation <sup>(1)</sup>	Source or Stockpile	One per 2000 tons, minimum of one per day.
		PI <sup>(1)</sup>		
<div>(1) Independent Assurance Sampling and Testing required.</div> <div>(2) Provided Construction &amp; Materials Group concurs, historical abrasion values may be used.</div>				

TABLE 3 ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MATERIAL				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1005	Recycling Agent RA-1 RA-5 RA-25 RA-75	Per Specifications	Circulation Line Recommended <sup>(4)</sup>	Certificate of Compliance required and duplicate samples (each one gallon in a metal can) per 1/2 shift.
1005	Liquid Asphalt [Cutback Asphalt - (Medium Curing Type)] MC-70 MC-250 MC-800 MC-3000	Per Specifications	Distributor Recommended <sup>(4)</sup>	Certificate of Compliance required and duplicate samples (each one gallon in a metal can) per delivery unit.
404	for Prime Coat			
<sup>(4)</sup> Point of sampling specified by Engineer. Note: During production, samples of bituminous material shall be taken by the contractor and witnessed by the Engineer.				

TABLE 3 (continued) ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MATERIAL				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1005	Emulsified Asphalt RS-1 CRS-1 RS-2 CRS-2 SS-1 CSS-1 CRS-2P	Per Specifications	Supplier (For pre-approval of material.)	See PPD <sup>(3)</sup> .
		Residue	Distributor Recommended <sup>(4)</sup>	See PPD <sup>(3)</sup> .
				For preapproved emulsions, Certificate of Compliance required and duplicate samples (each 1/2 gallon in a plastic container) per delivery unit.
404	for Chip Seal Coat, Tack Coat, and Fog Coat			For emulsions not preapproved, Certificate of Analysis required and duplicate samples (each 1/2 gallon in a plastic container) per delivery unit.
<p><sup>(3)</sup> ADOT Materials Practice and Procedure Directive.</p> <p><sup>(4)</sup> Point of sampling specified by Engineer.</p> <p>Note: During production, samples of bituminous material shall be taken by the contractor and witnessed by the Engineer.</p>				

TABLE 3 (continued) ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MATERIAL				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1005	Emulsified Asphalt Special Type (Diluted SS-1 or CSS-1)	Residue	Distributor Recommended <sup>(4)</sup>	See PPD <sup>(3)</sup> .
				For preapproved undiluted emulsions, Certificate of Compliance required and duplicate samples (each 1/2 gallon in a plastic container) per delivery unit.
404	for Tack Coat and Fog Coat			For undiluted emulsions not preapproved, Certificate of Analysis required and duplicate samples (each 1/2 gallon in a plastic container) per delivery unit.
<p><sup>(3)</sup> ADOT Materials Practice and Procedure Directive.</p> <p><sup>(4)</sup> Point of sampling specified by Engineer.</p> <p>Note: During production, samples of bituminous material shall be taken by the contractor and witnessed by the Engineer.</p>				

TABLE 3 (continued) ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MATERIAL				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1005	Asphalt Cement (PG XX-XX)	Per Specifications		
404	for Tack Coat			Certificate of Compliance required.
416 417	for Asphaltic Concrete		Supplier or Project	A two gallon sample (two full one-gallon metal cans) at least five days prior to start of asphaltic concrete production (for calibration of ignition furnace).
			Circulation Line Recommended <sup>(4)</sup>	
407 409 411 416 417	for Asphaltic Concrete, or ACFC		Supplier or Project	Certificate of Analysis and a one gallon sample in a metal can required at least seven days prior to start of asphaltic concrete production.
			Circulation Line Recommended <sup>(4)</sup>	
			Circulation Line Recommended <sup>(4)</sup>	Certificate of Compliance required and duplicate samples (each one gallon in a metal can) per 1/2 shift.
<sup>(4)</sup> Point of sampling specified by Engineer. Note: During production, samples of bituminous material shall be taken by the contractor and witnessed by the Engineer.				



TABLE 3 (continued) ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MATERIAL				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1005	Emulsified Recycling Agent (ERA) ERA-1 ERA-5 ERA-25 ERA-75	Per Specifications	Supplier (For pre- approval of material)	See PPD <sup>(3)</sup> .
		Residue	Distributor Recom- mended <sup>(4)</sup>	See PPD <sup>(3)</sup> .
				For preapproved ERA, Certificate of Compliance required and duplicate samples (each 1/2 gallon in a plastic container) per delivery unit.
				For ERA not preapproved, Certificate of Analysis required and duplicate samples (each 1/2 gallon in a plastic container) per delivery unit.
404	ERA (Diluted)	Residue	Distributor Recom- mended <sup>(4)</sup>	See PPD <sup>(3)</sup> .
	For preapproved undiluted ERA, Certificate of Compliance required and duplicate samples (each 1/2 gallon in a plastic container) per delivery unit.			
	For undiluted ERA not preapproved, Certificate of Analysis required and duplicate samples (each 1/2 gallon in a plastic container) per delivery unit.			
	for Fog Coat			

<sup>(3)</sup> ADOT Materials Practice and Procedure Directive.

<sup>(4)</sup> Point of sampling specified by Engineer.

Note: During production, samples of bituminous material shall be taken by the contractor and witnessed by the Engineer.

TABLE 3 (continued) ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MATERIAL				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1005 1009 410	Asphalt Cement (PG XX-XX) for Asphalt - Rubber (Sprayed Applications)	Per Specifications	Circulation Line - Delivery Unit	Certificate of Compliance required and duplicate samples (each one gallon in a metal can) for each shipment - not less than one set of duplicate samples for each 40 tons.
1005 1009 413 414 415	Asphalt Cement (PG XX-XX) for Asphalt - Rubber for AR-AC or AR-ACFC	Per Specifications	Delivery Unit Recommended <sup>(4)</sup>	Certificate of Compliance required and duplicate samples (each one gallon in a metal can) per 1/2 shift.
1009	Crumb Rubber for Asphalt - Rubber Type A or Type B	Gradation	Project	Certificate of Compliance required and one sample [approximately 1500 grams (one gallon) per Arizona Test Method 714] per lot per type.
1009 410	Asphalt - Rubber [CRA <sup>(5)</sup> ] Type 1, Type 2, or Type 3 (Sprayed Applications)	Per Special Provisions.	Distributor Recommended <sup>(4)</sup>	Certificate of Compliance required and a one gallon sample in a metal can per delivery unit.
<p><sup>(4)</sup> Point of sampling specified by Engineer.</p> <p><sup>(5)</sup> CRA = Crumb Rubber Asphalt</p> <p>Note: During production, samples of bituminous material shall be taken by the contractor and witnessed by the Engineer.</p>				

TABLE 3 (continued) ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MATERIAL				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1009 413 414 415	Asphalt - Rubber [CRA <sup>(5)</sup> ] Type 1, Type 2, or Type 3 For AR-AC or AR-ACFC	Penetration	Circulation Line Recom- mended <sup>(4)</sup>	Certificate of Compliance required.
		Softening Point		Duplicate samples (each one gallon in a metal can) per 1/2 shift.
		Resilience		
		Rotational Viscosity		
		Rotational Viscosity (at plant)		One sample (one gallon in a metal can) per batch.
415	for AR-AC		Supplier or Project	A two gallon sample (two full one-gallon metal cans) at least five days prior to start of asphaltic concrete production (for calibration of ignition furnace).
			Circulation Line Recom- mended <sup>(4)</sup>	
<div>(4) Point of sampling specified by Engineer.</div> <div>(5) CRA = Crumb Rubber Asphalt</div> <div>Note: During production, samples of bituminous material shall be taken by the contractor and witnessed by the Engineer.</div>				

TABLE 3 (continued) ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MATERIAL				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
Refer to Special Provisions	Emulsified Asphalt for Cold Recycled Asphaltic Concrete HFE-150P HFE-300P	Per Special Provisions.	Supplier (for pre- approval of material.)	See PPD <sup>(3)</sup> .
		Residue	Distributor Recom- mended <sup>(4)</sup>	See PPD <sup>(3)</sup> .
				For preapproved emulsions, Certificate of Compliance required and duplicate samples (each 1/2 gallon in a plastic container) per delivery unit.
				For emulsions not preapproved, Certificate of Analysis required and duplicate samples (each 1/2 gallon in a plastic container) per delivery unit.
<p><sup>(3)</sup> ADOT Materials Practice and Procedure Directive.</p> <p><sup>(4)</sup> Point of sampling specified by Engineer.</p> <p>Note: During production, samples of bituminous material shall be taken by the contractor and witnessed by the Engineer.</p>				

TABLE 4 ACCEPTANCE SAMPLING GUIDE FOR PORTLAND CEMENT CONCRETE				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
401 1006	Portland Cement Concrete (PCC) Class P	Compressive Strength <sup>(1)</sup>	Immediately before going into paver or forms, or as otherwise directed by the Engineer.	Five samples per lot. ----- (For compressive strength, one set of three cylinders per sample.)
		Slump		
		Air Content (when Required)		
		Temperature		
			Thickness	Roadway
1006	Portland Cement Concrete (PCC) Class S <b>(with a compressive strength requirement less than 4,000 psi)</b>	Compressive Strength <sup>(1)</sup>	At Discharge <sup>(6)</sup>	One sample for each 100 CY, or fraction thereof, of continuously placed concrete per day from each batch plant. For daily placements of 10 CY or less, at the discretion of the Engineer. ----- (For compressive strength, one set of two cylinders per sample.)
		Slump		
		Temperature		
			Air Content (when Required)	At Discharge <sup>(6)</sup>
<div><div>(1)</div><div>(6)</div></div> <div>Independent Assurance Sampling and Testing required.</div> <div>Concrete pumped to facilitate placement will be sampled for acceptance at the final point of placement. Samples will be taken during continuous discharge of concrete that has been pumped beyond the pump hopper without interruption at the normal production rate. Where freeze-thaw durability is of concern (such as in bridge decks, overlays, approach slabs, and barrier walls), the concrete shall also be sampled at the truck to determine air loss through the pump. In accordance with Subsection 601-3.03(C), if the loss of air as measured between the supply truck and the point of placement exceeds two percent, the contractor shall employ measures acceptable to the Engineer to reduce the loss of air to less than two percent. If sampling at the point of placement is not practical, as determined by the Engineer, or creates a safety concern, the concrete shall be sampled for acceptance at the truck. When acceptance sampling can only be performed at the truck, the acceptable range of air content of the supplied mix will be adjusted to not less than five percent nor more than eight percent in accordance with Subsection 1006-3.01.</div>				

TABLE 4 (continued) ACCEPTANCE SAMPLING GUIDE FOR PORTLAND CEMENT CONCRETE				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1006	Portland Cement Concrete (PCC) Class S <b>(with a compressive strength requirement equal to or greater than 4,000 psi)</b>	Compressive Strength <sup>(1)</sup>	At Discharge <sup>(6)</sup>	One sample for each 50 CY, or fraction thereof, of continuously placed concrete per day from each batch plant. For daily placements of 10 CY or less, at the discretion of the Engineer.  (For compressive strength, one set of three cylinders per sample.)
		Slump		
		Temperature		
		Air Content (when Required)	At Discharge <sup>(6)</sup>	Sample for air content every 50 CY when elevation is above 3000 ft. For daily placements of 10 CY or less, at the discretion of the Engineer.
<p>(1) Independent Assurance Sampling and Testing required.</p> <p>(6) Concrete pumped to facilitate placement will be sampled for acceptance at the final point of placement. Samples will be taken during continuous discharge of concrete that has been pumped beyond the pump hopper without interruption at the normal production rate. Where freeze-thaw durability is of concern (such as in bridge decks, overlays, approach slabs, and barrier walls), the concrete shall also be sampled at the truck to determine air loss through the pump. In accordance with Subsection 601-3.03(C), if the loss of air as measured between the supply truck and the point of placement exceeds two percent, the contractor shall employ measures acceptable to the Engineer to reduce the loss of air to less than two percent. If sampling at the point of placement is not practical, as determined by the Engineer, or creates a safety concern, the concrete shall be sampled for acceptance at the truck. When acceptance sampling can only be performed at the truck, the acceptable range of air content of the supplied mix will be adjusted to not less than five percent nor more than eight percent in accordance with Subsection 1006-3.01.</p>				

TABLE 4 (continued) ACCEPTANCE SAMPLING GUIDE FOR PORTLAND CEMENT CONCRETE				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1006	Portland Cement Concrete (PCC) Class B	Compressive Strength <sup>(1)</sup>	At Discharge <sup>(6)</sup>	One sample for each 100 CY of concrete placed from each batch plant For daily placements of 10 CY or less, at the discretion of the Engineer.
		Slump		
		Temperature		(For compressive strength, one set of two cylinders per sample.)
		Air Content (when Required)	At Discharge <sup>(6)</sup>	Sample for air content every 50 CY when elevation is above 3000 ft. For daily placements of 10 CY or less, at the discretion of the Engineer.
<p>(1) Independent Assurance Sampling and Testing required.</p> <p>(6) Concrete pumped to facilitate placement will be sampled for acceptance at the final point of placement. Samples will be taken during continuous discharge of concrete that has been pumped beyond the pump hopper without interruption at the normal production rate. Where freeze-thaw durability is of concern (such as in bridge decks, overlays, approach slabs, and barrier walls), the concrete shall also be sampled at the truck to determine air loss through the pump. In accordance with Subsection 601-3.03(C), if the loss of air as measured between the supply truck and the point of placement exceeds two percent, the contractor shall employ measures acceptable to the Engineer to reduce the loss of air to less than two percent. If sampling at the point of placement is not practical, as determined by the Engineer, or creates a safety concern, the concrete shall be sampled for acceptance at the truck. When acceptance sampling can only be performed at the truck, the acceptable range of air content of the supplied mix will be adjusted to not less than five percent nor more than eight percent in accordance with Subsection 1006-3.01.</p>				

TABLE 4 (continued) ACCEPTANCE SAMPLING GUIDE FOR PORTLAND CEMENT CONCRETE				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
601 1006	Portland Cement Structural Concrete for Minor Precast Structures (Manholes, Cattle Guards, Utility Vaults, Catch Basins, Flared Ends, etc.)	Rebound Hammer	At Fabrication Yard	One set of readings per precast unit.
601 1006	Prestressed Concrete	Compressive Strength	At Discharge <sup>(6)</sup>	One sample per member or for each day's production. (For compressive strength, a minimum of two sets of 3 cylinders for detensioning, and one set of 3 cylinders for 28-day breaks.)
		Slump		
		Temperature		
912	Shotcrete	Compressive Strength	Test Panels	Three cores from a test panel every 100 CY or fraction thereof, per day.
		Slump	At Mixer Discharge	One per 50 CY or fraction thereof, per day.
		Air Content (For Shotcrete placed at an elevation of 3,000 feet or above)	For wet-mix process, just prior to pumping For dry-mix process, from in-place material	
922 1006	Utility Concrete	None		
<sup>(6)</sup> Concrete pumped to facilitate placement will be sampled for acceptance at the final point of placement. Samples will be taken during continuous discharge of concrete that has been pumped beyond the pump hopper without interruption at the normal production rate. Where freeze-thaw durability is of concern (such as in bridge decks, overlays, approach slabs, and barrier walls), the concrete shall also be sampled at the truck to determine air loss through the pump. In accordance with Subsection 601-3.03(C), if the loss of air as measured between the supply truck and the point of placement exceeds two percent, the contractor shall employ measures acceptable to the Engineer to reduce the loss of air to less than two percent. If sampling at the point of placement is not practical, as determined by the Engineer, or creates a safety concern, the concrete shall be sampled for acceptance at the truck. When acceptance sampling can only be performed at the truck, the acceptable range of air content of the supplied mix will be adjusted to not less than five percent nor more than eight percent in accordance with Subsection 1006-3.01.				



TABLE 5 ACCEPTANCE SAMPLING GUIDE FOR MATERIALS USED WITH PORTLAND CEMENT CONCRETE				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
602 1003	Prestressing Steel (Spiral, Bars, Strand Wire, or Wire)	Tensile Strength	Project or Fabrication Plant	Certificate of Compliance required and one 6 ft. piece from each bar size, heat, reel, or coil.
602 1003	Post- Tensioning Steel	Tensile Strength	Project	Certificate of Compliance required and one 6 ft. piece from each bar size, heat, reel, or coil.
605 1003	Reinforcement Bars (Epoxy Coated or Uncoated)	Yield Strength, Tensile Strength, Bend Test, Elongation, Weight/Foot, and Coating Thickness (if applicable)		
	Phoenix and Tucson Sources		Fabrication Plant or Supplier's Yard	Certificate of Compliance required and samples as per PPD <sup>(3)</sup> .
			Project	Certificate of Compliance required and one 7 ft. bar per shipment. See PPD <sup>(3)</sup> .
	Other sources		Project	Certificate of Compliance required and samples as per PPD <sup>(3)</sup> .
1003	Welded Wire Fabric (Smooth)	Tensile Strength, Diameter, Spelter, Weld Shear, Reduction in Area	Supplier's Yard or Project	Certificate of Compliance required and one 2 ft. x 2 ft. sample per 25 rolls.
<sup>(3)</sup> ADOT Materials Practice and Procedure Directive.				

TABLE 5 (continued) ACCEPTANCE SAMPLING GUIDE FOR MATERIALS USED WITH PORTLAND CEMENT CONCRETE				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1003	Welded Wire Fabric (Deformed)	Tensile Strength, Weld Shear, Weight/Foot	Supplier's Yard or Project	Certificate of Compliance required and one 4 ft. x 4 ft. sample per 25 sheets.
1006	Admixtures			Certificate of Compliance required and must be on the Department's Approved Products List. See PPD <sup>(3)</sup> .
1006	Curing Compound	Water Loss	Supplier's Yard or Project	For material from preapproved lot, Certificate of Compliance only. See PPD <sup>(3)</sup> .
		% Solids		For material <u>not</u> preapproved, Certificate of Compliance and a 1/2 gallon sample per lot. See PPD <sup>(3)</sup> .
1006	Fly Ash and Natural Pozzolan	Chemical and Physical		Material supplied from an Approved Material Source. See PPD <sup>(3)</sup> .
1006	Silica Fume			Certificate of Compliance required with each delivery. See PPD <sup>(3)</sup> .
<sup>(3)</sup> ADOT Materials Practice and Procedure Directive.				

TABLE 5 (continued) ACCEPTANCE SAMPLING GUIDE FOR MATERIALS USED WITH PORTLAND CEMENT CONCRETE				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1006	Water	Soluble Salts ----- pH	Source	One sample (1 pint in glass container) per source <sup>(7)</sup> .
1006	Hydraulic Cement (All Types)	Chemical and Physical		Material supplied from an Approved Material Source. See PPD <sup>(3)</sup> .
1011	Joint Materials	Per Specifications		Silicone joint sealant must be on the Department's Approved Product List. In addition, a Certificate of Analysis shall accompany each lot or batch of sealant. ----- For joint materials other than silicone joint sealant, only a Certificate of Compliance is required.
<sup>(3)</sup> ADOT Materials Practice and Procedure Directive. <sup>(7)</sup> No sample is necessary if water is potable and comes from a proven source.				

TABLE 5 (continued) ACCEPTANCE SAMPLING GUIDE FOR MATERIALS USED WITH PORTLAND CEMENT CONCRETE				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1013 604	Bearing Pads (Preformed Fabric)	Thickness ----- Compression Load	Project	Certificate of Analysis required and two sample pads from every 100, or fraction thereof, with a minimum of one sample pad from each lot for each type of pad. (Tested by ADOT.)
1013 604	Bearing Pads (Plain and Fabric Reinforced Elastomeric)	Per Specification Subsection 1013-2	Project	Certificate of Analysis required and two sample pads from every 100, or fraction thereof, with a minimum of one sample pad from each lot for each type of pad. [Tested by Engineer approved testing laboratory. See PPD <sup>(3)</sup> .]
1013 604	Bearing Pads (Steel Reinforced Elastomeric)	Per Specification Subsection 1013-2	Project	Certificate of Analysis required and two sample pads from every 100, or fraction thereof, with a minimum of one sample pad from each lot for each type of pad. [Tested by Engineer approved testing laboratory. See PPD <sup>(3)</sup> .]
<sup>(3)</sup> ADOT Materials Practice and Procedure Directive.				

TABLE 6 ACCEPTANCE SAMPLING GUIDE FOR STABILIZED SOILS AND BASES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
301	Lime Treated Subgrade	Proctor Density	Roadway	One per soil type, and as needed.
		Optimum Moisture		
		Compaction	Roadway	One per lift per 1000 ft.
302	Cement Treated Subgrade	Proctor Density	Roadway	One per soil type, and as needed.
		Optimum Moisture		
		Compaction	Roadway	One per lift per 1000 ft.
304	Cement Treated Base	Proctor Density	Roadway	At start of production then one per week, and as needed.
		Optimum Moisture		
		Compaction	Roadway or Point of Placement	One per lift per 1000 ft.
		Compressive Strength <sup>(1)</sup>		Three random samples per shift. (Three specimens from each sample.)
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				

TABLE 6 (continued) ACCEPTANCE SAMPLING GUIDE FOR STABILIZED SOILS AND BASES				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
305	Lean Concrete Base	Compressive Strength <sup>(1)</sup>	At Discharge	Four random samples per 4000 SY, minimum four samples per shift.
		Slump		
		Air Content (when required)		
		Thickness	Roadway	Per Specifications.
Refer to Special Provisions	Bituminous Treated Base	See Special Provisions	Roadway	At the discretion of the Engineer.
Refer to Special Provisions	Cement Stabilized Alluvium	Compressive Strength <sup>(1)</sup>	Roadway or Point of Placement	One set of three per 1500 CY, minimum one set of three per 1/2 shift.
Refer to Special Provisions	Soil-Cement Bank Protection	Compressive Strength <sup>(1)</sup>	Roadway or Point of Placement	One set of three per 1500 CY, minimum one set of three per 1/2 shift.
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				

TABLE 7 ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MIXTURES				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
407	Asphaltic Concrete Friction Course (ACFC)	% Asphalt <sup>(1)</sup> ----- Moisture Content <sup>(1)</sup>	Trucks at Mixing Plant	1 per 1/2 shift.
409	Asphaltic Concrete (Miscellaneous Structural)  [For Special Mix, see below]	% Asphalt ----- Moisture Content ----- Rice ----- Marshall Density	Roadway	At the discretion of the Engineer.
409	Asphaltic Concrete (Miscellaneous Structural - Special Mix)	% Asphalt <sup>(1)</sup> ----- Moisture Content <sup>(1)</sup> ----- Rice <sup>(1)</sup> ----- Marshall Density <sup>(1)</sup> ----- Gradation <sup>(1)</sup>	Roadway	One sample per 500 tons.
411	Asphaltic Concrete Friction Course (ACFC) - Miscellaneous	% Asphalt ----- Moisture Content	Trucks at Mixing Plant	At the discretion of the Engineer.
413	Asphaltic Concrete (Asphalt – Rubber) [AR-AC]	% Asphalt-Rubber <sup>(1)</sup> ----- Moisture Content <sup>(1)</sup>	Roadway	4 per shift.
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				

TABLE 7 (continued) ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MIXTURES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
414	Asphaltic Concrete Friction Course (Asphalt – Rubber) [AR-ACFC]	% Asphalt- Rubber <sup>(1)</sup>	Trucks at Mixing Plant	4 per shift.
		----- Moisture Content <sup>(1)</sup>		
415	Asphaltic Concrete (Asphalt- Rubber) - End Product [AR-AC]	% Asphalt- Rubber <sup>(1)</sup>	Roadway	4 per lot.
		----- Moisture Content <sup>(1)</sup>		
		----- Gradation <sup>(1)</sup>		
		----- Marshall Density <sup>(1)</sup>		
		----- Rice <sup>(1)</sup>		
		----- Compaction	Roadway	20 cores per lot (10 locations/2 cores per location).
<sup>(1)</sup> Independent Assurance Sampling and Testing required.				



TABLE 7 (continued) ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MIXTURES				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
416	Asphaltic Concrete - End Product  [For mixes containing reclaimed asphalt pavement (RAP), see PPD <sup>(3)</sup> .]	% Asphalt <sup>(1)</sup>	Roadway	4 per lot.
		Moisture Content <sup>(1)</sup>		
		Gradation <sup>(1)</sup>		
		Marshall <sup>(1)</sup> [Density, Stability, and Flow]		
		Rice <sup>(1)</sup>		
		Compaction, unless otherwise specified. (Courses > 1½ inch in nominal thickness)	Roadway	20 cores per lot (10 locations/2 cores per location).
<sup>(1)</sup> Independent Assurance Sampling and Testing required.  <sup>(3)</sup> ADOT Materials Practice and Procedure Directive.				

TABLE 7 (continued) ACCEPTANCE SAMPLING GUIDE FOR BITUMINOUS MIXTURES				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
417	Asphaltic Concrete (End Product) SHRP Volumetric Mix  [For mixes containing reclaimed asphalt pavement (RAP), see PPD <sup>(3)</sup> .]	% Asphalt <sup>(1)</sup>	Roadway	4 per lot.
		Moisture Content <sup>(1)</sup>		
		Gradation <sup>(1)</sup>		
		Gyratory Density <sup>(1)</sup>		
		Rice <sup>(1)</sup>		
		Compaction (Courses > 1½ inch in nominal thickness)	Roadway	20 cores per lot (10 locations/2 cores per location).
Refer to Special Provisions	Asphaltic Concrete - Miscellaneous Paving			Tested at the discretion of the Engineer.
<sup>(1)</sup> Independent Assurance Sampling and Testing required. <sup>(3)</sup> ADOT Materials Practice and Procedure Directive.				

TABLE 8 ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
301 503 913 1010	Lime (for use in soil stabilization, mortar, and grout)	Chemical and Physical		See PPD <sup>(3)</sup> .
407 409 411 413 414 415 416 417	Hydrated Lime (for use as mineral admixture in asphaltic concrete mixes)			Material supplied from an Approved Material Source. See PPD <sup>(3)</sup> .
302 304 501 503 505 601 602 912 913 1010	Hydraulic Cement (for use in soil stabilization, mortar, and grout)	Chemical and Physical		See PPD <sup>(3)</sup> .
407 409 411 413 414 415 416 417	Portland Cement and Blended Hydraulic Cement (for use as mineral admixture in asphaltic concrete mixes)			Material supplied from an Approved Material Source. See PPD <sup>(3)</sup> .
<sup>(3)</sup> ADOT Materials Practice and Procedure Directive.				

TABLE 8 (continued) ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
501	Corrugated Metal Pipe (CMP) [Coated or Non-coated]	Yearly check by Central Lab	Supplier's Yard	Certificate of Compliance required.
501 1006	Non-Reinforced, Cast-in-Place Concrete Pipe	Compressive Strength	At Discharge <sup>(6)</sup>	Per Specifications.
		Slump		
		Air Content (when required)		
		Temperature		
		Wall Thickness	Site	
501 1010	Precast Reinforced or Non-Reinforced Concrete Pipe	Compression (D-Load)	Supplier's Yard	Certificate of Compliance required and one sample for each 100 sections per size per type.
		Wall Thickness		
Refer to Special Provisions	Vitrified Clay Pipe	Compression	Project	One sample for each 100 sections per size per type.
505	Brick for Manholes	Compression	Project	One sample (6 bricks of like kind and size) per project.
<sup>(6)</sup> Concrete pumped to facilitate placement will be sampled for acceptance at the final point of placement. Samples will be taken during continuous discharge of concrete that has been pumped beyond the pump hopper without interruption at the normal production rate. Where freeze-thaw durability is of concern (such as in bridge decks, overlays, approach slabs, and barrier walls), the concrete shall also be sampled at the truck to determine air loss through the pump. In accordance with Subsection 601-3.03(C), if the loss of air as measured between the supply truck and the point of placement exceeds two percent, the contractor shall employ measures acceptable to the Engineer to reduce the loss of air to less than two percent. If sampling at the point of placement is not practical, as determined by the Engineer, or creates a safety concern, the concrete shall be sampled for acceptance at the truck. When acceptance sampling can only be performed at the truck, the acceptable range of air content of the supplied mix will be adjusted to not less than five percent nor more than eight percent in accordance with Subsection 1006-3.01.				

TABLE 8 (continued) ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
Refer to Special Provisions	Paving Brick	Compression ----- Absorption	Project	One sample (6 paving bricks of like kind and size) per project.
Refer to Special Provisions	Cinder Block	Compression ----- Absorption	Project	One sample (6 cinder blocks of like kind and size) per project.
Refer to Special Provisions	Slump Block	Compression ----- Absorption	Project	One sample (6 slump blocks of like kind and size) per project.
604 731 1004 1012	High Strength Bolts, Nuts, Washers, or Anchor Bolts	Rockwell Hardness ----- Wedge Tensile Strength	Project	Certificate of Analysis required and three samples per lot, or 0.1% of lots in excess of 3000, for each bolt diameter, including nuts and washers.
608 1007	Retroreflective Sheeting	Per Specifications		Certificate of Compliance required and also must be on the Department's Approved Products List
608	Sign Panel Silk-Screened Characters			Certificate of Compliance required.

TABLE 8 (continued) ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
704 708 709	Glass Beads	Roundness	Supplier's Yard (Recom- mended) or Project	See PPD <sup>(3)</sup> .
		Gradation		=====
		Refractive Index		For other than Dual Component Pavement Markings:
		Moisture Resistance		Certificate of Compliance required*, and if preapproved, a copy of the Central Lab test results.
		Heavy Metal Concentration (if required)		If <u>not</u> preapproved by Central Lab, Certificate of Compliance required*, and a one gallon sample when material is supplied in a "super sack", or one full bag when material is supplied in a 50 pound bag.
				*If required, a Certificate of Analysis must also be submitted (certifying that the Heavy Metal Concentration meets the specifications).
				=====
				For Dual Component Pavement Markings:
				=====
				Certificate of Analysis required**, and if preapproved, a copy of the Central Lab test results.
				=====
				If <u>not</u> preapproved by Central Lab, Certificate of Analysis required**, and a one gallon sample when material is supplied in a "super sack", or one full bag when material is supplied in a 50 pound bag.
				=====
				**The Certificate of Analysis shall also include a Material Safety Data Sheet (MSDS).

<sup>(3)</sup> ADOT Materials Practice and Procedure Directive.

TABLE 8 (continued) ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
705	Preformed Plastic Pavement Marking			<p>Certificate of Compliance required*, and also must be on the Department's Approved Products List.</p> <p>*A Certificate of Analysis is also required (certifying that the Heavy Metal Concentration of the glass beads meets the specifications).</p>
704	Thermoplastic Pavement Markings	Per Specifications	Supplier or Contractor	At the discretion of the Engineer, a sample (one gallon in a metal can) of the material from each batch or, alternatively, sufficient material from one or more bags of material to make a representative one gallon sample, may be submitted to Central Lab for testing prior to use.
			Project	Certificate of Compliance and, if applicable, a copy of the Central Materials Chemistry Lab test results are required. Also must be on the Department's Approved Products List.
				Random spot checks for thickness of thermoplastic material while being applied.

TABLE 8 (continued) ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
706	Raised Pavement Markers	Per Specifications	Project	Certificate of Compliance required for markers and adhesive.
				Adhesive must be on the Department's Approved Products List.
				For non-reflective pavement markers, one sample (one marker) per lot per type.
				For reflective pavement markers, one sample (three markers) per lot per type.
708	Permanent Pavement Markings (Painted)	Per Specifications	Supplier or Contractor	A sample (one quart in a metal can) of the material from each batch must be submitted to Central Lab for testing prior to use.
			Project	Certificate of Compliance and a copy of the Central Materials Chemistry Lab test results are required.
				Check-samples of finished paint while being applied, at intervals determined by the Engineer.



TABLE 8 (continued) ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
709	Dual Component Pavement Markings	Per Specifications	Project	Certificate of Analysis required and must be on the Department's Approved Projects List. ----- Random spot checks for thickness.
732	Polyvinyl Chloride (PVC) Pipe for Electrical Conduit	Resistance to Crushing	Project	One sample per 5000 ft.
808	Polyvinyl Chloride (PVC) Pipe for Water	Wall Thickness ----- Burst Pressure ----- Diameter	Project	One sample per 10,000 ft.
902	Chain Link Fabric			Certificate of Compliance required.
902	Fence Post and Rails			Certificate of Compliance required.
902 903	Miscellaneous Fence Hardware			Certificate of Compliance required.
902 903	Post Clips, Hog Rings, Tie Wire, or Tension Wire			Certificate of Compliance required.

TABLE 8 (continued) ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
903	Barbed Wire or Barbless Wire	Tensile Strength ----- Spelter ----- Diameter	Supplier's Yard or Project	Certificate of Compliance <sup>(8)</sup> required and one 4 ft. sample per 50 rolls.
903	Fence Stays			Certificate of Compliance required.
903	T-Post	Weight/Foot ----- Length	Supplier's Yard or Project	Certificate of Compliance <sup>(8)</sup> required and one post per 500 posts, or fraction thereof, per lot.
903	Woven Wire Fabric	Spelter ----- Diameter ----- Tensile Strength	Supplier's Yard or Project	Certificate of Compliance <sup>(8)</sup> required and one sample [3 feet long, the full height (width) of the fabric] per 50 rolls.
904 913	Wire Rope			Certificate of Compliance required.
<sup>(8)</sup> Certifying that manufacturing processes and application of coating occurred in the United States. (This certification required for Federal-Aid projects only. See Special Provisions for exception based on quantity being used.)				

TABLE 8 (continued) ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFICATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1002	Paint	Per Specifications	Project	Paint for use on structural steel and other metallic surfaces:
				Certificate of Compliance is required and the system must be on the Department's Approved Products List.
			=====	
			Supplier or Contractor	Paint for use on concrete or masonry surfaces:
				A sample (one quart in a metal can) of the material from each batch must be submitted to Central Lab for testing prior to use.
			Project	Certificate of Compliance and a copy of the Central Materials Chemistry Lab test results are required. Also must be on the Department's Approved Products List.
			=====	
			Project	Paint for use on other than structural steel and other metallic surfaces, concrete surfaces, or masonry surfaces:
				Certificate of Compliance is required and one sample (one quart in a metal can) per batch submitted to Central Lab for testing.

TABLE 8 (continued) ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1012	Guardrail Elements			Certificate of Compliance required.
1012	Guardrail Fasteners	Rockwell Hardness	Project	For other than High Strength Anchor Bolts, Certificate of Compliance required and three samples per lot, or 0.1% of lots in excess of 3000, for each bolt diameter, including nuts and washers.
		Tensile Strength		For High Strength Anchor Bolts, see Page 51.
1012	Guardrail Posts and Blocks	None		Certificate of Compliance required.
				For timber guardrail posts and blocks, see PPD <sup>(3)</sup> .
<sup>(3)</sup> ADOT Materials Practice and Procedure Directive.				

TABLE 8 (continued) ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
1014	Geosynthetics		Supplier and Project	If material has been preapproved, Certificate of Compliance required and one sample for every 10 rolls per lot. (Minimum of one sample per lot.) Samples shall not be taken within 5 feet from either end of the roll, and shall be at least 6 feet long by the full width of the roll.
			Project	If material has <u>not</u> been preapproved, Certificate of Analysis required and one sample for every 10 rolls per lot. (Minimum of one sample per lot.) Samples shall not be taken within 5 feet from either end of the roll, and shall be at least 6 feet long by the full width of the roll.
NOTE: Information on Geosynthetics continued on next page.				

TABLE 8 (continued) ACCEPTANCE SAMPLING GUIDE FOR MISCELLANEOUS MATERIALS				
SPECIFI- CATION SECTION	MATERIAL	TYPE OF TEST(S) REQUIRED	SAMPLING POINT	MINIMUM SAMPLING FREQUENCY
NOTE: Information on Geosynthetics continued from previous page.				
1014 412	Pavement Fabric	Per Specification Subsection 1014-2		
1014 306	Geogrid	Per Specification Subsection 1014-3		
1014 208	Separation Geotextile Fabric	Per Specification Subsection 1014-4		
1014 913	Bank Protection Fabric	Per Specification Subsection 1014-5		
1014 203	Geocomposite Wall Drain System	Per Specification Subsection 1014-6		
1014 307	Geocomposite Edge Drain System	Per Specification Subsection 1014-7		
208	Geomembrane	See Special Provisions.		

### Sample Ticket

**PLEASE PRESS FIRMLY  
WHILE FILLING OUT FORM**

**USE CAPITAL LETTERS**

LAB NUMBER

ORQ NUMBER

MATL

TYPE

PUR-  
POSE

TEST  
LAB

SIZE

SIZE %

TEST NO.

LOT OR  
SUFFIX

SAMPLED BY

MO

DAY

YEAR

TIME

MILITARY  
TIME

SAMPLED FROM

LIFT NO.

RDWY

STATION

ORIGINAL SOURCE

PROJECT ENGINEER /  
SUPERVISOR

PROJECT NUMBER

TRACS NUMBER

REMARKS

IF MILEPOST, INPUT DECIMAL

## Testing Lab Codes

A Acceptance  
M Miscellaneous  
C Control  
P Independent Assurance  
I Informational

C Central Lab  
R Regional Lab  
P Project Lab

## Roadway Codes

Stockpiles:

- B Blend
- F Fine
- I Intermediate
- C Coarse
- K Coarsest

Bins:

- 9 Composite of Bins
- 1 Bin #1
- 2 Bin #2, etc.

NB	Northbound
SB	Southbound, etc.
RA	Ramp A
RB	Ramp B, etc.
FR	Frontage Road
XR	Crossroad

TABLE 10  
LISTING OF MATERIAL CODES AND TYPE CODES  
USED BY FAST [Field Office Automation System]<sup>(9)</sup>

Material Description	Material Code	Type Description	Type Code
Admix	AD		
Aggregate	AG	Bituminous Treated Base	BB
Aggregate	AG	Cement Treated Base	CB
Aggregate	AG	Cement Treated Subgrade	CS
Aggregate	AG	Lean Concrete Base	LC
Aggregate	AG	Lime Treated Subgrade	LS
Aggregate	AG	Road Mix	RM
Aggregate	AG	Soil Cement	SC
Aggregate Base	AB	Class 1	1
Aggregate Base	AB	Class 2	2
Aggregate Base	AB	Class 3	3
Aggregate Subbase	AS	Class 4	4
Aggregate Subbase	AS	Class 5	5
Aggregate Subbase	AS	Class 6	6
Arrestor Bed Aggregate	AA		
Asphaltic Concrete	AC	1/2" Asphaltic Concrete	12
Asphaltic Concrete	AC	1/2" Fine Band 417 AC	12F
Asphaltic Concrete	AC	1/2" Coarse Band 417 AC	12K
Asphaltic Concrete	AC	3/4" Asphaltic Concrete	34
Asphaltic Concrete	AC	3/4" Fine Band 417 AC	34F
Asphaltic Concrete	AC	3/4" Coarse Band 417 AC	34K
Asphaltic Concrete	AC	Asphaltic Concrete Friction Course (ACFC)	FC
Asphaltic Concrete	AC	Asphalt-Rubber Asphaltic Concrete (AR-AC)	RD
Asphaltic Concrete	AC	Asphalt-Rubber Asphaltic Concrete Friction Course (AR-ACFC)	RF
Asphaltic Concrete	AC	Base Mix	BM
Asphaltic Concrete	AC	Bituminous Treated Base	BB
Asphaltic Concrete	AC	AZ409 Miscellaneous Structural	409MI
Asphaltic Concrete	AC	AZ409 Miscellaneous Structural (Special Mix)	409SP

<sup>(9)</sup> FAST may revise codes, delete codes, or add codes at various times. Users must assure that they are utilizing the current FAST codes.



TABLE 10 (continued) LISTING OF MATERIAL CODES AND TYPE CODES USED BY FAST [Field Office Automation System] <sup>(9)</sup>			
Material Description	Material Code	Type Description	Type Code
Asphaltic Concrete	AC	Other	OT
Asphaltic Concrete	AC	Recycled Asphaltic Concrete	RC
Asphaltic Concrete	AC	Road Mix	RM
Asphaltic Concrete Friction Course (ACFC)	FC		
Asphalt-Rubber Asphaltic Concrete (AR-AC)	RD		
Asphalt-Rubber Asphaltic Concrete Friction Course (AR-ACFC)	RF		
Backfill	BF	Aluminum Pipe	AP
Backfill	BF	Concrete Pipe	CP
Backfill	BF	Metal Pipe	MP
Backfill	BF	Plastic Pipe	PP
Backfill	BF	Slurry	SL
Backfill	BF	Special	SP
Backfill	BF	Trench	TR
Bedding Material	BM	Concrete Pipe	CP
Bedding Material	BM	Corrugated Metal Pipe	MP
Bedding Material	BM	PVC Pipe	PV
Bedding Material	BM	Slurry	SL
Blotter Material	BL		
Borrow	BW		
Cement Stabilized Alluvium	CS		
Coarse Aggregate	CA	Size 1	1
Coarse Aggregate	CA	Size 2	2
Coarse Aggregate	CA	Size 3	3
Coarse Aggregate	CA	Size 4	4
Coarse Aggregate	CA	Size 5	5
Coarse Aggregate	CA	Size 6	6
Coarse Aggregate	CA	Size 7	7
Coarse Aggregate	CA	Size 8	8
Coarse Aggregate	CA	Size 9	9
<sup>(9)</sup> FAST may revise codes, delete codes, or add codes at various times. Users must assure that they are utilizing the current FAST codes.			

TABLE 10 (continued) LISTING OF MATERIAL CODES AND TYPE CODES USED BY FAST [Field Office Automation System] <sup>(9)</sup>			
Material Description	Material Code	Type Description	Type Code
Coarse Aggregate	CA	Size 10	10
Coarse Aggregate	CA	Size 24	24
Coarse Aggregate	CA	Size 56	56
Coarse Aggregate	CA	Size 57	57
Coarse Aggregate	CA	Size 67	67
Coarse Aggregate	CA	Size 68	68
Coarse Aggregate	CA	Size 78	78
Coarse Aggregate	CA	Size 89	89
Coarse Aggregate	CA	Size 357	357
Coarse Aggregate	CA	Size 467	467
Coarse Aggregate	CA	Composite Samples	NA
Cover Material	CM		
Crash Barrel Sand	CB		
Decomposed Granite	DG		
Embankment	EM		
Entrained Air (Air Content)	ET		
Filter Material	FM		
Fine Aggregate	FA		
Fly Ash	FF		
Granite Mulch	GM		
Granulated (Crumb) Rubber	GR		
Grout	GT		
Maintenance	MT		
Membrane Seal	MS		
Mineral Aggregate	MA		
Mineral Aggregate	MA	1/2" Asphaltic Concrete	12
Mineral Aggregate	MA	1/2" Fine Band 417 AC	12F
Mineral Aggregate	MA	1/2" Coarse Band 417 AC	12K
Mineral Aggregate	MA	3/4" Asphaltic Concrete	34
Mineral Aggregate	MA	3/4" Fine Band 417 AC	34F
Mineral Aggregate	MA	3/4" Coarse Band 417 AC	34K
Mineral Aggregate	MA	AZ409 Miscellaneous Structural	409MI
Mineral Aggregate	MA	AZ409 Miscellaneous Structural (Special Mix)	409SP
<sup>(9)</sup> FAST may revise codes, delete codes, or add codes at various times. Users must assure that they are utilizing the current FAST codes.			

TABLE 10 (continued) LISTING OF MATERIAL CODES AND TYPE CODES USED BY FAST [Field Office Automation System] <sup>(9)</sup>			
Material Description	Material Code	Type Description	Type Code
Mineral Aggregate	MA	Asphaltic Concrete Friction Course (ACFC)	FC
Mineral Aggregate	MA	Asphalt-Rubber Asphaltic Concrete (AR-AC)	RD
Mineral Aggregate	MA	Asphalt-Rubber Asphaltic Concrete Friction Course (AR-ACFC)	RF
Mineral Aggregate	MA	Base Mix	BM
Mineral Aggregate	MA	Other	OT
Mineral Aggregate	MA	Recycled Asphaltic Concrete	RC
Natural Ground	NG		
Other	OT		
Pipe Plating	PM		
Pneumatically Placed Mortar	NM		
Reclaimed Asphalt Pavement	RP	Coarse	C
Reclaimed Asphalt Pavement	RP	Fine	F
Reclaimed Asphalt Pavement	RP	Other	O
Rip Rap	RR		
Rock Mulch	RM		
Slurry	SL	3/8" Aggregate	38
Slurry	SL	#4 Aggregate	4
Structure Backfill	SB		
Subgrade	SG		
Subgrade Seal	SS		
Top Soil	TS		
Water	HO		
Winter Cinders	WC		
<sup>(9)</sup> FAST may revise codes, delete codes, or add codes at various times. Users must assure that they are utilizing the current FAST codes.			

TABLE 11 INDEX OF MATERIALS LISTED IN TABLES 1 THROUGH 8	
MATERIAL	PAGE
Admixtures for Portland Cement Concrete	40
Aggregate for Arrestor Bed	26
Aggregate for Cement Stabilized Alluvium	26
Aggregate for Cement Treated Base	9
Aggregate for Lean Concrete Base	9
Aggregate for Soil-Cement Bank Protection	26
Aggregate Base	5-6
Aggregate Subbase	7-8
Asphalt Cement (PG XX-XX)	30
Asphalt Cement (PG XX-XX) for Asphalt-Rubber	32
Asphaltic Concrete (Asphalt-Rubber) [AR-AC]	45
Asphaltic Concrete (Asphalt-Rubber) - End Product [AR-AC]	46
Asphaltic Concrete - End Product	47
Asphaltic Concrete (End Product) SHRP Volumetric Mix	48
Asphaltic Concrete Friction Course (ACFC)	45
Asphaltic Concrete Friction Course (Asphalt-Rubber) [AR-ACFC]	46
Asphaltic Concrete Friction Course (ACFC) - Miscellaneous	45
Asphaltic Concrete - Miscellaneous Paving	48
Asphaltic Concrete (Miscellaneous Structural)	45
Asphaltic Concrete (Miscellaneous Structural - Special Mix)	45
Asphalt-Rubber (CRA)	32-33
Bank Protection Fabric	60
Barbed Wire	56
Barbless Wire	56
Bearing Pads	42
Bedding Material for Pipe	21
Bedding Material for Polyvinyl Chloride (PVC) Irrigation Pipe	22
Bituminous Treated Base	44
Blotter Material	10
Borrow	1
Brick for Manholes	50
Cement Stabilized Alluvium	44
Cement Treated Base	43
Cement Treated Subgrade	43
Chain Link Fabric	55
Cinder Block	51

TABLE 11 (continued) INDEX OF MATERIALS LISTED IN TABLES 1 THROUGH 8	
MATERIAL	PAGE
Coarse Aggregate for Portland Cement Concrete (PCC)	25
Cover Material	10
Crash Barrel Sand	22
Crumb Rubber for Asphalt-Rubber	32
Curing Compound	40
Decomposed Granite	3
Dual Component Pavement Markings	55
Embankment	1
Emulsified Asphalt	28
Emulsified Asphalt Special Type	29
Emulsified Asphalt for Cold Recycled Asphaltic Concrete	34
Emulsified Recycling Agent (ERA)	31
Fence Hardware, Miscellaneous	55
Fence Post and Rails	55
Fence Stays	56
Filter Material for Perforated Pipe	21
Fine Aggregate for Portland Cement Concrete (PCC)	24
Fly Ash and Natural Pozzolan	40
Geocomposite Edge Drain System	60
Geocomposite Wall Drain System	60
Geogrid	60
Geomembrane	60
Geosynthetics	59-60
Glass Beads	52
Granite Mulch	3
Guardrail Elements	58
Guardrail Fasteners	58
Guardrail Posts and Blocks	58
High Strength Bolts, Nuts, Washers, or Anchor Bolts	51
Hydrated Lime (for use as mineral admixture in asphaltic concrete mixes)	49
Hydraulic Cement	41
Hydraulic Cement (for use in soil stabilization, mortar, and grout)	49
Joint Materials	41
Lean Concrete Base	44
Lime (for use in soil stabilization, mortar, and grout)	49
Lime Treated Subgrade	43
Liquid Asphalt [Cutback Asphalt - (Medium Curing Type)]	27

TABLE 11 (continued) INDEX OF MATERIALS LISTED IN TABLES 1 THROUGH 8	
MATERIAL	PAGE
Mineral Aggregate for Asphaltic Concrete (Asphalt-Rubber) [AR-AC]	14
Mineral Aggregate for Asphaltic Concrete (Asphalt-Rubber) – End Product [AR-AC]	16
Mineral Aggregate for Asphaltic Concrete - End Product [without reclaimed asphaltic pavement (RAP)]	17
Mineral Aggregate for Asphaltic Concrete - End Product [with reclaimed asphaltic pavement (RAP)]	18
Mineral Aggregate for Asphaltic Concrete (End Product) SHRP Volumetric Mix [without reclaimed asphalt pavement (RAP)]	19
Mineral Aggregate for Asphaltic Concrete (End Product) SHRP Volumetric Mix [without reclaimed asphalt pavement (RAP)]	20
Mineral Aggregate for Asphaltic Concrete Friction Course (ACFC)	12
Mineral Aggregate for Asphaltic Concrete Friction Course (Asphalt-Rubber) [AR-ACFC]	15
Mineral Aggregate for Asphaltic Concrete Friction Course (ACFC) - Miscellaneous	14
Mineral Aggregate for Asphaltic Concrete - Miscellaneous Paving	21
Mineral Aggregate for Asphaltic Concrete (Miscellaneous Structural)	13
Mineral Aggregate for Asphaltic Concrete (Miscellaneous Structural – Special Mix)	13
Mineral Aggregate for Micro-Surfacing	11
Natural Ground	1
Paint	57
Pavement Fabric	60
Paving Brick	51
Permanent Pavement Markings (Painted)	54
Pipe Backfill	4
Pipe, Corrugated Metal (CMP) [Coated or Non-coated]	50
Pipe, Non-Reinforced Cast-in-Place Concrete	50
Pipe, Polyvinyl Chloride (PVC) for Electrical Conduit	55
Pipe, Polyvinyl Chloride (PVC) for Water	55
Pipe, Precast Reinforced or Non-Reinforced Concrete	50
Pipe, Vitrified Clay	50
Plating Material for Pipe Ends	22
Portland Cement and Blended Hydraulic Cement (for use as mineral admixture in asphaltic concrete mixes)	49
Portland Cement Concrete (PCC) (Class P)	35

TABLE 11 (continued) INDEX OF MATERIALS LISTED IN TABLES 1 THROUGH 8	
MATERIAL	PAGE
Portland Cement Concrete (PCC) (Class S) (with a compressive strength requirement less than 4,000 psi)	35
Portland Cement Concrete (PCC) (Class S) (with a compressive strength requirement equal to or greater than 4,000 psi)	36
Portland Cement Concrete (PCC) (Class B)	37
Portland Cement Structural Concrete for Minor Precast Structures	38
Post Clips and Hog Rings	55
Post-Tensioning Steel	39
Preformed Plastic Pavement Marking	53
Prestressed Concrete	38
Prestressing Steel	39
Raised Pavement Markers	54
Recycling Agent	27
Reinforcement Bars	39
Retroreflective Sheeting	51
Rock	23
Shotcrete	38
Sign Panel Silk-Screened Characters	51
Silica Fume	40
Slump Block	51
Soil for Shoulder Build-up	2
Soil-Cement Bank Protection	44
Separation Geotextile Fabric	60
Structure Backfill	4
Subgrade	2
T-Post	56
Thermoplastic Pavement Markings	53
Tie Wire and Tension Wire	55
Top Soil	3
Trench Backfill	2
Utility Concrete	38
Water	41
Welded Wire Fabric (Smooth)	39
Welded Wire Fabric (Deformed)	40
Wire Rope	56
Woven Wire Fabric	56